

MOR4






MOR4.1 layer too thin almost nothing visible. 1 in the assumed area with R 1 measurement outside

MOR4.2 magnification increased. 2 measurements on two residues

Sample: MOR4.1

Type: Default




Element	Weight%	Atomic%	
C K	36.55	47.80	
O K	41.65	40.89	
Mg K	0.33	0.21	
Al K	3.78	2.20	
Si K	12.53	7.01	
P K	0.39	0.20	
S K	0.46	0.22	
K K	1.12	0.45	
Ca K	1.03	0.40	
Fe K	2.16	0.61	
Totals	100.00		



Sample: MOR4.1

Type: Default


Element	Weight%	Atomic%	
C K	32.60	43.68	
O K	41.13	41.37	
Al K	0.37	0.22	
Si K	25.30	14.50	
K K	0.11	0.04	
Ca K	0.49	0.20	
Totals	100.00		





Sample: MOR4.2

Type: Default

Element	Weight%	Atomic%	
C K	55.71	65.84	
O K	31.58	28.01	
Al K	0.69	0.36	
Si K	9.55	4.83	
S K	0.72	0.32	
Cl K	0.40	0.16	
K K	0.22	0.08	
Ca K	1.12	0.40	
Totals	100.00		




Quantitative results



Sample: MOR4.2

Type: Default

Element	Weight%	Atomic%	
C K	54.28	64.55	
O K	32.69	29.19	
Al K	0.82	0.44	
Si K	9.22	4.69	
S K	0.61	0.27	
Cl K	0.37	0.15	
K K	0.42	0.15	
Ca K	1.58	0.56	
Totals	100.00		



Quantitative results

